

Parameter	Unit	LA	HA	DC
Total Solids Content	% Min	61.0	61.5	60.0
Dry Rubber Content	% Min	60.0	60.0	59.0
Non-rubber Solids	% Max	2.0	2.0	2.0
Ammonia	% on Latex	0.2 – 0.3	Min 0.6	0.15 – 0.25
Mechanical Stability	s, Min	650	650	650
Coagulum Content	% Max	0.03	0.03	0.03
Copper	ppm Max	8	8	8
Manganese	ppm Max	8	8	8
Sludge Content	% Max	0.1	0.1	0.1